

ARMY RESEARCH LABORATORY



Interceptor Small Arms Protective Insert (SAPI) MANTECH Product Enhancement Test Report I

by Jeffrey A. Mears, Robert F. Monks, Robert Wolffe,
and James F. Mackiewicz

ARL-CR-487

February 2002

prepared by

Jeffrey A. Mears, Robert F. Monks, and Robert Wolffe
Simula Safety Systems Inc.
7822 South 46th Street
Phoenix, AZ 85044

James F. Mackiewicz
U.S. Army Natick Soldier Center
AMSSB-RIP-MC(N)
Natick, MA 01760-5011

under contract

DAAN02-98-D-5007-003

Approved for public release; distribution is unlimited.

20020328 035

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Citation of manufacturer's or trade names does not constitute an official endorsement or approval of the use thereof.

Destroy this report when it is no longer needed. Do not return it to the originator.

Army Research Laboratory

Aberdeen Proving Ground, MD 21005-5069

ARL-CR-487

February 2002



Interceptor Small Arms Protective Insert (SAPI) MANTECH Product Enhancement Test Report I

Jeffrey A. Mears, Robert F. Monks, and Robert Wolffe
Simula Safety Systems Inc.

James F. Mackiewicz
U.S. Army Natick Soldier Center

prepared by

Simula Safety Systems Inc.
7822 South 46th Street
Phoenix, AZ 85044

U.S. Army Natick Soldier Center
AMSSB-RIP-MC(N)
Natick, MA 01760-5011

under contract

DAAN02-98-D-5007-003

Approved for public release; distribution is unlimited.

Abstract

This report summarizes the work performed by Specialty Plastics Products of Pennsylvania Inc. and their subcontractor, Simula Safety Systems Inc., under the Manufacturing Technology (MANTECH) program sponsored by the U.S. Army Materiel Command and executed by the U.S. Army Natick Soldier Center. The objective of this effort was to investigate armor materials and processes that could potentially provide cost reductions to the multi-Service Interceptor Small Arms Protective Inserts (SAPI).

Contents

List of Tables	v
1. Introduction	1
2. SAPI First Article Test (FAT) Optimization Testing	2
2.1 Quasi-Isotropic Laminate	2
2.2 Fiberglass/SS Hybrid Laminate	2
2.3 Kevlar/SS Hybrid Laminate	3
2.4 Kevlar/SS Hybrid Laminate V_0 Testing	4
2.5 Graphite/SS Hybrid Laminate	5
2.6 SS Plus Laminate	5
2.7 Thicker Tile/Standard Laminate	6
2.8 Warp-to-Fill Laminate	7
2.9 Fill-to-Fill Laminate	7
2.10 Increased SS	8
2.11 CERCOM Powder Process Tile	9
2.12 CERCOM Tape Process Tile	9
2.13 Increased Laminate Armor System	10
2.14 Increased Tile Armor System	10
2.15 Kevlar/SS Hybrid Armor System	11
2.16 Double-Process Laminate	11
2.17 Kevlar/SS/Kevlar Hybrid Armor System	12
3. Further SAPI Optimization Efforts	13
3.1 KM2 Polyethylene Film Stack Laminate	13
3.2 KM2 Mark III Laminate	14
4. Conclusions	15

Distribution List	17
Report Documentation Page	23

List of Tables

Table 1. V_{50} testing with 46-ply 0/+45/-45 SS backings.....	2
Table 2. V_{50} testing with 42-ply SS/1-ply fiberglass backings.	3
Table 3. V_{50} testing with 44-ply SS/1-ply Kevlar backings.	3
Table 4. V_0 threat A FAT preparation (Kevlar hybrid).....	4
Table 5. V_{50} testing with 44-ply SS/graphite hybrid backings.....	5
Table 6. V_{50} testing with 61-ply SS Plus backings.	6
Table 7. V_{50} testing with thicker tile and standard laminate.	6
Table 8. V_{50} testing with warp face to fill face laminate.....	7
Table 9. V_{50} testing with fill face to fill face laminate.	8
Table 10. V_{50} testing with three additional SS plies.	8
Table 11. V_{50} testing with powder-processed tile.....	9
Table 12. V_{50} testing with tape-processed tile.....	10
Table 13. V_{50} testing with increased laminate armor system.	10
Table 14. V_{50} testing with increased areal density armor system.	11
Table 15. V_{50} testing with Kevlar/SS hybrid armor system.	12
Table 16. V_{50} testing with double-processed laminate.	12
Table 17. V_{50} testing with Kevlar/SS/Kevlar hybrid armor system.	13
Table 18. V_{50} testing with 22-ply KM2/polyethylene film-stacked backings.	14
Table 19. V_{50} testing with 21-ply KM2 Mark III backings.....	14

INTENTIONALLY LEFT BLANK.

1. Introduction

As described in U.S. Army Materiel Command Acquisition Center (USAMCAC) Contract No. DAAN02-98-D-5007-003, line item 0004, Manufacturing Technology (MANTECH) statement of work, the contractor shall investigate materials and material processes that will potentially provide cost reduction benefits to the U.S. Marine Corps and the U.S. Army. The scope of work included the following tasks:

- Fabricate and ballistically test at least five small arms protective insert (SAPI) products with cost-reduction composite materials. The composite backing systems will be fabricated in conjunction with the currently used Spectra Shield (SS) composite backing in an array configuration to be determined by the contractor. The lower-cost fiber reinforced plastic (FRP) materials to be experimentally tested will include Kevlar 49 and Kevlar 29 (KRP), glass-reinforced plastic (GRP), and Spectra-reinforced plastic (SRP).
- Investigate SAPI fabrication parameters, which shall expeditiously process the greatest number of quality inserts per run. Processing parameters for investigation shall include time, temperature, pressure, and volume. Evaluation of the most efficient combination of parameters shall be validated through Government nondestructive analysis and ballistic testing.
- Coordinate with Government personnel (U.S. Army Natick Soldier Center, U.S. Army Aberdeen Test Center [ATC], and U.S. Army Research Laboratory [ARL]) to correlate nondestructive prototype confirmation testing to reduce the costs associated with ballistic destructive testing. If feasible, implement nondestructive production lot acceptance testing as part of cost-reduction acceptance criteria.
- Submit findings of the previously mentioned tasks, and any additional tasks that are paid for by MANTECH funds under this delivery order, in a final report to the project officers. The final report shall be submitted in the contractor's format and must be delivered within 30 days of completion of MANTECH studies under this delivery order. All efforts under this delivery order and the submittal of the final report must occur no later than 1 December 1999.
- The final report shall be submitted to the project officers via e-mail in Microsoft Word 6.0 or higher.

This document will summarize the efforts involved in developing the design to meet the current Interceptor SAPI requirements.

2. SAPI First Article Test (FAT) Optimization Testing

The following testing was accomplished in an attempt to optimize the SAPI design in order to meet or exceed the FAT requirements outlined in the SAPI performance specification. These tests were performed in February–April 1999.

2.1 Quasi-Isotropic Laminate

It has been shown in some of the soft body armor work, that by alternating the ply orientation between 0°, 90°, +45°, and -45° increased ballistic performance can be achieved. We fabricated six specimens of 0.210-in tile with 46 plies SS in a quasi-isotropic layup. The targets had an areal density of 3.95 psf. These specimens were tested for V₅₀ with threat A on 28-ply KM2 600 denier backings. The results for this series are shown in Table 1.

Table 1. V₅₀ testing with 46-ply 0/+45/-45 SS backings.

Shot No.	Velocity (fps)	Result
1	2885	CP
2	2899	CP
3	2748	CP
4	2699	CP
5	2568	PP

Notes: CP = complete penetration.

PP = partial penetration.

The 46-ply quasi-isotropic SS test series resulted in a V₅₀ of 2633 fps (2 shot) with a 131-fps spread. This was below the acceptable V₅₀ requirement; therefore, this laminate design was not considered for further testing.

2.2 Fiberglass/SS Hybrid Laminate

It has been shown in metal/composite armor system testing that adding 1 ply of fiberglass between the metal and SS improves the ballistic performance. We fabricated six specimens of 0.210-in tile with 1 ply of fiberglass/epoxy and 42 plies of SS. The targets had an areal density of 4.03 psf. These specimens were tested for V₅₀ with threat A on 28-ply KM2 600 denier backings. The results for this series are shown in Table 2.

Table 2. V_{50} testing with 42-ply SS/1-ply fiberglass backings.

Shot No.	Velocity (fps)	Result
1	2887	CP
2	2854	PP
3	2855	PP
4	2969	CP
5	2948	CP
6	2929	PP

The 42-ply SS/1-ply fiberglass test series resulted in V_{50} of 2907 fps (6 shot) with a 115-fps spread. The addition of the fiberglass produced marginal improvements with an increase in the material cost and plate complexity; therefore, this laminate design was not considered for further testing.

2.3 Kevlar/SS Hybrid Laminate

Past ballistic data indicate that a hybrid of Kevlar and SS will increase ballistic performance. We fabricated six specimens of 0.210-in tile with 1 ply of Kevlar/epoxy and 44 plies of SS. The targets had an areal density of 4.04 psf. These specimens were tested for V_{50} with threat A on 28-ply KM2 600 denier backings. The results for this series are shown in Table 3.

Table 3. V_{50} testing with 44-ply SS/1-ply Kevlar backings.

Shot No.	Velocity (fps)	Result
1	2843	PP
2	2977	PP
3	3050	PP
4	3097	CP
5	3061	PP
6	3075	PP

The 44-ply SS/1-ply Kevlar test series resulted in a V_{50} of 3086 fps (2 shot) with a 22-fps spread. The addition of the Kevlar produced an improvement in the V_{50} performance; therefore, this laminate design was considered for further testing.

2.4 Kevlar/SS Hybrid Laminate V_0 Testing

In order to evaluate the Kevlar/SS hybrid laminate, we prepared five SAPI plates using production tiles (0.210 in minimum) with the 1-ply Kevlar and 46 plies of SS. The plates had a nominal areal density of 4.10 psf (without durability covers). The results for this series are shown in Table 4.

Table 4. V_0 threat A FAT preparation (Kevlar hybrid).

Sample No.	Velocity (fps)	Obliquity (°)	Result	BFD (in)
1	2787	0	PP	1.38
1	2780	0	PP	1.38
1	2796	30	PP	1.25
2	2763	0	PP	1.38
2	2786	0	CP	N/A
2	2797	30	PP	1.38
3	2796	0	PP	1.60
3	2795	0	PP	1.70
3	2781	30	PP	1.40
4	2639	0	PP	1.38
4	2777	0	PP	1.62
4	2767	30	PP	1.38
5	2785	0	PP	1.50
5	2787	0	CP	N/A

Notes: BFD = back face deformation.

N/A = not applicable.

As shown in Table 4, this design resulted in two complete penetrations (2786 fps and 2787 fps) which would not satisfy the performance requirements; therefore, additional testing was required.

2.5 Graphite/SS Hybrid Laminate

After discussions with Simula Safety Systems Inc. (Simula)* we concluded that we should investigate the use of graphite/epoxy[†] as a hybrid material with the SS PCR material. The graphite/epoxy is much stiffer than either the fiberglass or the Kevlar/epoxy and as such will provide more support to the ceramic tile during the ballistic impact event. We fabricated six specimens of 0.210-in tile with a ply of graphite/epoxy and 44 plies of SS. The targets had an areal density of 4.03 psf. These specimens were tested for V_{50} with threat A on 28-ply KM2 600 denier backings. The results for this series are shown in Table 5.

Table 5. V_{50} testing with 44-ply SS/graphite hybrid backings.

Shot No.	Velocity (fps)	Result
1	2902	PP
2	2943	PP
3	3051	PP
4	3062	CP
5	3061	PP
6	3133	CP

The 44-ply SS/graphite hybrid test series resulted in a V_{50} of 3076 fps (4 shot) with an 82-fps spread. This result was similar to the V_{50} that was obtained using the Kevlar/SS hybrid laminate. Due to the expensive nature of the graphite/epoxy material, we decided to look at other alternatives for armor system designs.

2.6 SS Plus Laminate

Honeywell supplied samples of SS PCR Plus,[‡] which they report exhibits increased ballistic performance over standard SS PCR.[‡] We fabricated six specimens of 0.210-in tile with 61 plies of SS PCR Plus. The targets had an areal density of 4.09 psf. These specimens were tested for V_{50} with threat A on 28-ply KM2 600 denier backings. The results for this series are shown in Table 6.

*Simula Safety Systems Inc., Applied Technology Division, 7822 S. 46th Street, Phoenix, AZ 85044.

[†]Simula Product No. (P/N) 102906-2HL.

[‡]SS PCR and SS PCR Plus are Honeywell Company registered tradenames for types of Spectra Shield ballistic laminates.

Table 6. V_{50} testing with 61-ply SS Plus backings.

Shot No.	Velocity (fps)	Result
1	2868	PP
2	2945	CP
3	2934	PP
4	2953	PP
5	2940	PP
6	3011	PP

The 61-ply SS Plus test series resulted in a V_{50} of 2978 fps (2 shot) with a 66-fps spread. The change to SS Plus produced marginal improvements, with an increase in the material cost and plate complexity; therefore, this laminate design was not considered for further testing.

2.7 Thicker Tile/Standard Laminate

We investigated an increased areal density armor system to see how performance would be affected. We looked at thicker tile with the same laminate and fabricated six specimens of 0.250-in tile with 43 plies of SS PCR. The targets had an areal density of 4.47 psf. These specimens were tested for V_{50} with threat A on 28-ply KM2 600 denier backings. The results for this series are shown in Table 7.

Table 7. V_{50} testing with thicker tile and standard laminate.

Shot No.	Velocity (fps)	Result
1	2836	PP
2	2953	PP
3	2999	PP
4	3142	CP
5	3110	PP
6	3158	CP

The thicker tile/standard laminate test series resulted in a V_{50} of 3150 fps (2 shot-reverse) with a 16-fps spread. While this armor system produced a good V_{50} value, we did not have authorization to increase the areal density of the SAPI system at this time, so this design was no longer considered.

2.8 Warp-to-Fill Laminate

We investigated the effect of how the laminate is laid up prior to autoclave cure. The supplier of the SS material, Allied Signal, specified that the material be laid up warp face to fill face (where every ply is laid on the previous ply just as it is oriented on the roll) prior to autoclave or press cure. We fabricated six specimens of 0.210-in tile with 43 plies of SS PCR warp face to fill face. The targets had an areal density of 3.95 psf. These specimens were tested for V_{50} with threat A on 28-ply KM2 600 denier backings. The results for this series are shown in Table 8.

Table 8. V_{50} testing with warp face to fill face laminate.

Shot No.	Velocity (fps)	Result
1	2857	PP
2	2958	CP
3	2864	PP
4	2934	PP
5	2942	PP
6	2951	PP

The warp face to fill face laminate test series resulted in a V_{50} of 2954 fps (2 shot) with a 7-fps spread. This result was consistent with the baseline test results.

2.9 Fill-to-Fill Laminate

We wanted to see how the test results would vary from the previous test series if the laminates were laid up fill face to fill face (where every other ply is flipped). We fabricated six specimens of 0.210-in tile with 43 plies of SS PCR fill face to fill face. The targets had an areal density of 3.95 psf. These specimens were tested for V_{50} with threat A on 28-ply KM2 600 denier backings. The results for this series are shown in Table 9.

The fill face to fill face laminate test series resulted in a V_{50} of 2940 fps (4 shot) with a 37-fps spread. This test indicated that the layup sequence has no effect on the ballistic performance of the armor system.

Table 9. V_{50} testing with fill face to fill face laminate.

Shot No.	Velocity (fps)	Result
1	2816	PP
2	2960	CP
3	2896	PP
4	2942	CP
5	2935	PP
6	2923	PP

2.10 Increased SS

We investigated a slightly thicker laminate with three more plies of SS PCR. We fabricated six specimens of 0.210-in tile with 46 plies of SS PCR. The targets had an areal density of 4.03 psf. These specimens were tested for V_{50} with threat A on 28-ply KM2 600 denier backings. The results for this series are shown in Table 10.

Table 10. V_{50} testing with three additional SS plies.

Shot No.	Velocity (fps)	Result
1	2912	PP
2	2862	CP
3	2791	PP
4	2775	CP
5	2933	PP
6	2957	PP

The increased laminate thickness test series resulted in a V_{50} of 2826 fps (2 shot) with a 71-fps spread. This was below the acceptable V_{50} requirement; therefore, this laminate design was not considered for further testing.

2.11 CERCOM Powder Process Tile

CERCOM Inc.* (CERCOM) supplied samples of boron carbide (B_4C) tile that were produced using a hot pressing operation starting with a powder charge in the mold, which is the standard method of producing large billets of this material. We fabricated six specimens of 0.210-in tile with 46 plies of SS PCR. The targets had an areal density of 4.03 psf. These specimens were tested for V_{50} with threat A on 28-ply KM2 600 denier backings. The results for this series are shown in Table 11.

Table 11. V_{50} testing with powder-processed tile.

Shot No.	Velocity (fps)	Result
1	2964	CP
2	2840	PP
3	2896	PP
4	2853	PP
5	3000	CP
6	2917	CP

The powder process tile test series resulted in a V_{50} of 2907 fps (4 shot) with a 111-fps spread. This result was consistent with the baseline test results.

2.12 CERCOM Tape Process Tile

CERCOM supplied samples of B_4C tile that were produced using a hot pressing operation starting with a tape-laid charge in the mold. The use of this method of tile fabrication will lower the cost of fabricating the production tile. We fabricated six specimens of 0.210-in tile with 46 plies of SS PCR. The targets had an areal density of 4.03 psf. These specimens were tested for V_{50} with threat A on 28-ply KM2 600 denier backings. The results for this series are shown in Table 12.

The tape process tile test series resulted in a V_{50} of 3100 fps (2 shot) with a 55-fps spread. This test indicated that the tape process for producing tile has a positive effect on the ballistic performance of the armor system.

*CERCOM Inc., 991 Park Center Drive, Vista, CA 92083.

Table 12. V_{50} testing with tape-processed tile.

Shot No.	Velocity (fps)	Result
1	2739	PP
2	2811	PP
3	2899	PP
4	3046	PP
5	3073	PP
6	3128	CP

2.13 Increased Laminate Armor System

The areal density requirement of the armor system was increased from 4.0 to 4.8 psf. We investigated the increase by adding additional SS, and raising the minimum tile thickness from 0.210 to 0.230 in. We fabricated six specimens of 0.230-in tile with 64 plies of SS PCR. The targets had an areal density of 4.78 psf. These specimens were tested for V_{50} with threat A on 28-ply KM2 600 denier backings. The results for this series are shown in Table 13.

Table 13. V_{50} testing with increased laminate armor system.

Shot No.	Velocity (fps)	Result
1	2866	PP
2	2928	PP
3	2958	CP
4	2965	CP
5	2966	PP
6	2943	CP

The increased laminate test series resulted in a V_{50} of 2948 fps (4 shot) with a 38-fps spread. For V_{50} testing, this increase in armor system areal density did not seem to have any effect on the armor system performance.

2.14 Increased Tile Armor System

The areal density requirement of the armor system was increased from 4.0 to 4.8 psf. We investigated the increase by increasing the tile thickness from 0.210

to 0.280 in and decreasing the laminate from 43 to 40 plies of SS. We fabricated six specimens of 0.280-in tile with 40 plies of SS PCR. The targets had an areal density of 4.79 psf. These specimens were tested for V_{50} with threat A on 28-ply KM2 600 denier backings. The results for this series are shown in Table 14.

Table 14. V_{50} testing with increased areal density armor system.

Shot No.	Velocity (fps)	Result
1	2866	PP
2	2928	PP
3	2958	CP
4	2965	CP
5	2966	PP
6	2943	CP

The increased tile test series resulted in a V_{50} of 3002 fps (4 shot) with a 93-fps spread. The armor system seemed to increase in ballistic performance when the tile was increased.

2.15 Kevlar/SS Hybrid Armor System

Since the areal density requirement of the armor system was increased from 4.0 to 4.8 psf and the thicker tile test series produced a high V_{50} , we revisited the Kevlar/SS hybrid armor system. We fabricated six specimens of 0.280-in tile with 36 plies of SS PCR/1-ply Kevlar epoxy hybrid laminates. The targets had an areal density of 4.74 psf. These specimens were tested for V_{50} with threat A on 28-ply KM2 600 denier backings. The results for this series are shown in Table 15.

The Kevlar/SS test series resulted in a V_{50} of 3020 fps (2 shot) with a 13-fps spread. This result was consistent with the baseline increased areal density test results.

2.16 Double-Process Laminate

During the original FAT testing, we noticed that some of the test specimens performed better than others. After investigation, we found that the specimens that performed better ballistically, had been processed in the autoclave twice due

Table 15. V_{50} testing with Kevlar/SS hybrid armor system.

Shot No.	Velocity (fps)	Result
1	2930	PP
2	3033	CP
3	2898	PP
4	3014	PP
5	3027	CP
6	2770	PP

to a vacuum bag malfunction. In order to investigate this phenomena, we fabricated six specimens of 0.230-in tile with 46 plies of SS PCR, and ran the targets through the autoclave twice. The targets had an areal density of 4.29 psf. These specimens were tested for V_{50} with threat A on 28-ply KM2 600 denier backings. The results for this series are shown in Table 16.

Table 16. V_{50} testing with double-processed laminate.

Shot No.	Velocity (fps)	Result
1	2783	PP
2	2749	PP
3	2879	PP
4	2904	PP
5	3002	CP
6	2984	CP

The double-process laminate test series resulted in a V_{50} of 2944 fps (2 shot) with an 80-fps spread. These results did not prove that the double processing enhanced the ballistic performance of the armor system; therefore, no further investigation was warranted.

2.17 Kevlar/SS/Kevlar Hybrid Armor System

Past studies have shown that support of the ceramic material provides increased ballistic performance. We investigated a hybrid using KM2 fabric impregnated with vinyl-ester (VE) resin to provide support as well as ballistic resistance, SS to provide a tough middle layer, and KM2 polyurethane as a stiff ballistic back

face. We fabricated six specimens of 0.280-in tile with 4-ply KM2 VE/22-ply SS PCR/5-ply KM2 film stack hybrid laminates. The targets had an areal density of 4.87 psf. These specimens were tested for V_{50} with threat A on 28-ply KM2 600 denier backings. The results for this series are shown in Table 17.

Table 17. V_{50} testing with Kevlar/SS/Kevlar hybrid armor system.

Shot No.	Velocity (fps)	Result
1	2774	PP
2	2851	PP
3	2970	PP
4	3003	CP
5	2790	PP
6	2832	PP

The Kevlar/SS/Kevlar test series resulted in a V_{50} of 2986 fps (2 shot) with a 33-fps spread. These results did not prove that the Kevlar/SS/Kevlar hybrid enhanced the ballistic performance of the armor system, no further investigation was warranted. The result of this testing is the current SAPI design of 0.270 ± 0.020 in B₄C on 45 plies of SS, processed at 250 psi and 250 °F for 2 hr.

3. Further SAPI Optimization Efforts

At this point, we investigated a non-Spectra-based laminate backing. We chose two contending materials: KM2 film stacked with polyethylene and KM2 Mark III supplied by DuPont. This testing was performed at Simula Technologies Inc.* ballistic test facilities during August 2000.

3.1 KM2 Polyethylene Film Stack Laminate

The use of the KM2 600 denier (film stacked with polyethylene) would provide a stiff, supportive yet ballistically viable composite backing, so we tested a KM2 polyethylene film stack laminate. We fabricated six specimens of 0.272-in tile with 22 plies of KM2 (850 denier style 705) and 23 plies polyethylene film

*Simula Technologies Inc., is the parent organization of Simula Safety Systems, Inc. (a wholly owned subsidiary).

(0.001 in). The targets had an areal density of 4.78 psf. These specimens were tested for V_{50} with threat A on 28-ply KM2 600 denier backings. The results for this series are shown in Table 18.

Table 18. V_{50} testing with 22-ply KM2/polyethylene film-stacked backings.

Shot No.	Velocity (fps)	Result
1	2746	PP
2	2938	PP
3	2901	PP
4	3006	PP
5	3142	CP
6	3079	PP

The 22-ply KM2/polyethylene test series resulted in a V_{50} of 3110 fps (2 shot) with a 63-fps spread.

3.2 KM2 Mark III Laminate

The use of the KM2 (Style 705) Mark III will provide a stiff, supportive, yet ballistically viable, composite backing. We tested a KM2 Mark III laminate and fabricated six specimens of 0.272-in tile with 21 plies of KM2 (850 denier style 705) Mark III material supplied by DuPont. The targets had an areal density of 4.81 psf. These specimens were tested for V_{50} with threat A on 28-ply KM2 600 denier backings. The results for this series are shown in Table 19.

Table 19. V_{50} testing with 21-ply KM2 Mark III backings.

Shot No.	Velocity (fps)	Result
1	2831	PP
2	2918	CP
3	2853	PP
4	2884	PP
5	2900	PP
6	2843	PP

The 22-ply KM2 Mark III test series resulted in a V_{50} of 2909 fps (2 shot) with an 18-fps spread.

4. Conclusions

After testing various laminate backings, the all-SS option proved to be the most desirable from a cost and performance standpoint. By the time we began investigating the KM2 film stack and KM2 Mark III options, we had already identified a new ceramic material supplied by M Cubed Technologies Inc. of Newark, DE. This new ceramic material is a "reaction bonded" silicone carbide that can be produced to tighter tolerances at a much lower cost compared to the hot-pressed B_4C material. We were directed and funded to perform another MANTECH effort (delivery order 9)¹ to investigate the use of this new ceramic material for the Interceptor program. Based on this information, the baseline B_4C /SS armor system remains as 0.270 ± 0.020 -in B_4C on 45 plies of SS PCR bonded at 25 psi and 250 °F for 2 hr.

¹Mears, J. A., R. F. Monks, R. Wolffe, and J. F. Mackiewicz. "Interceptor Small Arms Protective Insert (SAPI) MANTECH Product Enhancement Test Report II." ARL-CR-488, U.S. Army Research Laboratory, Aberdeen Proving Ground, MD, February 2002.

INTENTIONALLY LEFT BLANK.

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	DEFENSE TECHNICAL INFORMATION CENTER DTIC OCA 8725 JOHN J KINGMAN RD STE 0944 FT BELVOIR VA 22060-6218
1	HQDA DAMO FDT 400 ARMY PENTAGON WASHINGTON DC 20310-0460
1	OSD OUSD(A&T)/ODDR&E(R) DR R J TREW 3800 DEFENSE PENTAGON WASHINGTON DC 20301-3800
1	COMMANDING GENERAL US ARMY MATERIEL CMD AMCRDA TF 5001 EISENHOWER AVE ALEXANDRIA VA 22333-0001
1	INST FOR ADVNCD TCHNLGY THE UNIV OF TEXAS AT AUSTIN 3925 W BRAKER LN STE 400 AUSTIN TX 78759-5316
1	US MILITARY ACADEMY MATH SCI CTR EXCELLENCE MADN MATH THAYER HALL WEST POINT NY 10996-1786
1	DIRECTOR US ARMY RESEARCH LAB AMSRL D DR D SMITH 2800 POWDER MILL RD ADELPHI MD 20783-1197
1	DIRECTOR US ARMY RESEARCH LAB AMSRL CI AI R 2800 POWDER MILL RD ADELPHI MD 20783-1197

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
3	DIRECTOR US ARMY RESEARCH LAB AMSRL CI LL 2800 POWDER MILL RD ADELPHI MD 20783-1197
3	DIRECTOR US ARMY RESEARCH LAB AMSRL CI IS T 2800 POWDER MILL RD ADELPHI MD 20783-1197
	<u>ABERDEEN PROVING GROUND</u>
2	DIR USARL AMSRL CI LP (BLDG 305)

NO. OF
COPIES ORGANIZATION

1 DIR USARL
AMSRL SS
2800 POWDER MILL RD
ADELPHI MD 20783-1145

1 CDR
AMXRO RT
OFC RSRCH &
TECH INTEGRATION
PO BOX 12211
RESEARCH TRIANGLE PARK NC
27709-2211

1 CDR
AMXRO RM
DR J BAILEY
PO BOX 12211
RESEARCH TRIANGLE PARK NC
27709-2211

1 CDR
CAMERON STATION
DTIC FDAC
BLDG 5
5010 DUKE ST
ALEXANDRIA VA 22304

1 DPTY CG FOR RDE
US ARMY MATERIEL CMD
AMCRDA TF
5001 EISENHOWER AVE
ALEXANDRIA VA 22333-0001

1 CDR
USA ARDEC
AMSTA ARCCHC
M DANESI
PICATINNY ARSENAL NJ
07806-5000

1 ARMY NATIONAL
GUARD BUREAU
NGB ARO O
LTC M NICKELL
111 S GEORGE MASON DR
ARLINGTON VA 22204-1382

1 US ARMY MEDICAL
MATERIAL
MCMR MMC B
1423 SULTAN DR STE 100
FT DETRICK MD 21702-5001

NO. OF
COPIES ORGANIZATION

1 CDR
NATICK SC
USA NATICK SOLDIER CTR
TECHNICAL LIBRARY
NATICK MA 01760-5019

15 CDR
NATICK SOLDIER CTR
J MACKIEWICZ
KANSAS ST
NATICK MA 01760-5010

1 CDR
NATICK SOLDIER CTR
P BRANDLER
KANSAS ST
NATICK MA 01760-5010

1 CDR
NATICK SOLDIER CTR
B G MADDOX
KANSAS ST
NATICK MA 01760-5010

1 CDR
USA TANK AUTO CMD
AMSTA TSL
TECHNICAL LIBRARY
WARREN MI 48397-5000

1 DIR
DEFENSE INTEL AGCY
ODT 5A
WASHINGTON DC 20340-6053

1 NAVAL RESEARCH LAB
DR R BADALIANCE
CODE 6684
4555 OVERLOOK AVE SW
WASHINGTON DC 20375

1 CDR
AIFRTC
G SCHLESINGER
APPL TECH BR
220 7TH ST NE
CHARLOTTESVILLE VA 22901-5396

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	CDR USA QUARTERMASTER SCHOOL QUARTERMASTER SCHOOL LIBRARY FT LEE VA 23801
1	CDR USA ARDEC AMSTA AR AET DR W EBIHARA PICATINNY ARSENAL NJ 07806
1	CDR NAWCAD UNIT 7 BLDG 439 STE F 47110 LILJENCRAVANTZ RD PATUXENT RIVER MD 20670-1545
1	DIR OF MILITARY SUPPORT DAMO ODC COMPIO 400 ARMY PENTAGON WASHINGTON DC 20310-0400
1	PM SPECIAL PROJECTS MAJ A EARLE 5951 PUTNAM RD FT BELVOIR VA 22060-5424
3	PM SOLDIER COL JETTE LTC BADELLE (2 CPS) FORT BELVOIR VA 22060
1	JTCG AS CENTRAL OFFICE NAVAL AIR SYSTEMS CMD AIR 418 J JOLLEY 1421 JEFFERSON HIGHWAY ARLINGTON VA 22243-5120
2	CDR US ARMY INFANTRY CENTER COL HOLTON (2 CPS) FORT BENNING GA 31905-5400

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	US MILITARY POLICE SCHOOL ATZN MP CM J KOCIABA FORT MCCLELLAN AL 36205-5030
5	NATIONAL INSTITUTE OF JUSTICE OFFICE OF LAW ENFORCEMENT K HIGGINS (5 CPS) BLDG 225 RM A323 GAITHERSBURG MD 20899
11	COMMANDING GENERAL MARINE CORPS SYSTEMS CMD CODE CMCC B G FAIGLEY B G DONOVAN LTC BELL LTC NELSON D BRYCE CPT CHURCH MAJ PATRICIO (5 CPS) 22033 BARNETT AVE STE 315 QUANTICO VA 22134-5080
1	PROJECT MANAGER AIRCREW INTEGRATED SYS SFAE AV LSE P CROUCH BLDG 5681 RM 151 REDSTONE ARSENAL AL 35898
2	CDR US ARMY TACOM AMSTA TRS J THOMPSON S GOODMAN WARREN MI 48397-5000
2	HQDA SARD TR R MORRISON R ROHDE 2511 JEFFERSON DAVIS HWY STE 9800 ARLINGTON VA 22202-3911
1	HQDA OASA RDA SARD SC RM 3C468 WASHINGTON DC 20310-0103

NO. OF
COPIES ORGANIZATION

1 HQDA
SARDA TD
DR C CHURCH
WASHINGTON DC 20310

1 CARDEROCK DIVISION HQS
DAVID TAYLOR MDL BASIN
R PETERSON
BETHESDA MD 20084-5000

2 US ARMY MATERIEL CMD
AMCDCG T C W KITCHENS
AMCRDA TF C GARDINIER
5001 EISENHOWER AVE
ALEXANDRIA VA 22333-0001

1 NAVAL SPECIAL WARFARE
DEVELOPMENT GROUP
CODE N51
B DEPPEN
1636 REGULUS AVE
VIRGINIA BEACH VA 23461-2299

1 US SECRET SERVICE DIV
TECHNICAL SECURITY
T THOMAS
1800 G ST NW
WASHINGTON DC 20223

1 CDR
MARINE CORPS LOGISTICS BASES
CODE 835 NBC
814 RADFORD BLVD
ALBANY GA 31704-112

3 SIMULA SAFETY SYSTEMS INC
S LYONS
J MEIRS
R MONKS
7822 S 46TH ST
PHOENIX AZ 85044

2 CDR NGIC
IANG GS MT MS306
J CRIDER
W GSTATTENBAUER
2055 BOULDERS ROAD
CHARLOTTESVILLE VA
22901-8318

NO. OF
COPIES ORGANIZATION

1 CIA
OSWR DSD
W WALTMAN
RM 5P0110 NHB
WASHINGTON DC 20505

2 DIR LLNL
R GOGOLEWSKI MS L290
J REAUGH
PO BOX 808
LIVERMORE CA 94550

1 DIR LLNL
R LANDINGHAM L32
PO BOX 808
LIVERMORE CA 94550

2 DIR LANL
F ADDESSIO
M BURKETT
LOS ALAMOS NM 87545

1 DIR SNL
D GRADY MS 0821
PO BOX 5800
ALBUQUERQUE NM 87185-0307

1 DIR SNL
M FORRESTAL DIV 1551
PO BOX 5800
ALBUQUERQUE NM 87185-0307

2 DIR SNL
R BRANNON MS 0820
M KIPP MS 0820
PO BOX 5800
ALBUQUERQUE NM 87185

1 DSC PHILADELPHIA
DSCP FNSE
2800 SOUTH 20TH ST
PHILADELPHIA PA 19145-5099

NO. OF
COPIES ORGANIZATION

- 1 CDR NSWC
MD11
DAHLGREN DIV
17320 DAHLGREN RD
DAHLGREN VA 22448-5100
- 4 USSOCOM
HQ USSOCOM
SOAL T SAREN
SOAL SP PULLAR
COL KEENAN
T MORRISSEY
7701 TAMPA PT BLVD
MACDILL AFB FL 33621-5323
- 1 USSOCOM
HQ USSOCOM
ANNEX 501B
M IVERSON
7701 TAMPA PT BLVD
MACDILL AFB FL 33621-5323

ABERDEEN PROVING GROUND

- 1 US ARMY DEV TEST CTR
CSTE DTC TT S T KOCHER
314 LONGS CORNER RD
APG MD 21005
- 5 US ARMY ATC
CSTE DTC AT CO
COL BROWN (5 CPS)
400 COLLERAN RD
APG MD 21005
- 15 US ARMY ATC
CSTE DTC AT SL
COL ELLIS (5 CPS)
C VALZ (5 CPS)
V W BLETHEN (5 CPS)
400 COLLERAN RD
APG MD 21005
- 5 DIR USARL
AMSRL WM
J SMITH
AMSRL WM TA
W GOOCH
W GILLICH
W BRUCHEY
AMSRL WM TD
T HADUCH

INTENTIONALLY LEFT BLANK.

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
<small>Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.</small>				
1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE February 2002		3. REPORT TYPE AND DATES COVERED Final, February 1999–April 1999
4. TITLE AND SUBTITLE Interceptor Small Arms Protective Insert (SAPI) MANTECH Product Enhancement Test Report I				5. FUNDING NUMBERS C: DAAN02-98-D-5007-003
6. AUTHOR(S) Jeffrey A. Mears,* Robert F. Monks,* Robert Wolffe,* and James F. Mackiewicz†				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Simula Safety Systems Inc. 7822 South 46th Street Phoenix, AZ 85044				8. PERFORMING ORGANIZATION REPORT NUMBER
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) U.S. Army Natick Soldier Center AMSSB-RIP-MC(N) Natick, MA 01760-5011				10. SPONSORING/MONITORING AGENCY REPORT NUMBER ARL-CR-487
11. SUPPLEMENTARY NOTES *Simula Safety Systems Inc., Phoenix, AZ 85044. †U.S. Army Natick Soldier Center, Natick, MA 01760-5011. The POC for this report is Dana Granville, USARL, ATTN: AMSRL-WM-MB, APG, MD 21005-5069.				
12a. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution is unlimited.				12b. DISTRIBUTION CODE
13. ABSTRACT (Maximum 200 words) This report summarizes the work performed by Specialty Plastics Products of Pennsylvania Inc. and their subcontractor, Simula Safety Systems Inc., under the Manufacturing Technology (MANTECH) program sponsored by the U.S. Army Materiel Command and executed by the U.S. Army Natick Soldier Center. The objective of this effort was to investigate armor materials and processes that could potentially provide cost reductions to the multi-Service Interceptor Small Arms Protective Inserts (SAPI).				
14. SUBJECT TERMS interceptor, SAPI, light armor, protective vest, composite armor				15. NUMBER OF PAGES 26
				16. PRICE CODE
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT UL	

INTENTIONALLY LEFT BLANK.